

Product Code: SXMSGGA290W

Description: SX Mighty Strength Grip & Grab Adhesive Cartridge



**Benefits**

- High initial grab - to bond heavy building materials without the use of clamps and/or fixing tape
- High strength, high E-modulus and high mechanical resistance, anti-pick and burglar proof
- Durable elasticity and fast curing
- No shrinkage and bubble free
- Non corrosive to metals
- Neutral curing, almost odourless
- Good resistance to weather and water
- Adheres perfectly without primer on most, even damp surfaces
- Free of isocyanates, solvents and silicones
- Absorbs acoustic and mechanical vibrations

**Application**

Suitable for bonding most building substrates but in particular, for fixing of large panels, wallboards and mirrors. Ideal for bonding brick slips, claddings and sanitary fixtures. Can also be used to fix dado rails, windowsills and decorative mouldings; it will adhere to virtually everything including wood, stone, mirrors, concrete, metal, mortar, bricks, gypsum and glass.

**Directions Of Use**

Cut the cartridge seal and screw on the pre-cut 'V' notched nozzle which must be used to ensure correct depth of adhesive is extruded.  
We recommend that a good quality skeleton gun is used due to that, by its nature, the product is stiff to gun. Apply the adhesive on one surface only in vertical strips, approximately 10 - 20cm apart. Immediately place item into position with good, even pressure to give an excellent initial grab.  
On extremely heavy items, temporary support may be necessary during the curing process. Mechanical fixings should always be used in overhead applications.

**Limitations**

Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates  
Not suitable for continuous exposure to water  
Not suitable for movement joints  
Not suitable in combination with chlorides (pools)

**Cleaning**

Cured material can only be mechanically removed. Hands can be cleaned with SX Multi-Purpose Cleaning Wipes.

**Additional Information**

100% Modulus	DIN 53504 S2	1.39 N/mm <sup>2</sup>
Application Rate	@ Ø2.5 mm/6.3 bar	20 g/min
Application Temperature		+5°C to +40°C
Base		Hybrid
Flow	ISO 7390	<2mm
Curing Time	+ 23°C / 50% RH	2-3
Density	ISO 1183-1	1.57 g/ml
Elongation at Break	DIN 53504 S2	335%
Frost Resistance During Transportation		Down to -15°C
Tensile Strength	DIN 53504 S2	2.20 N/mm <sup>2</sup>
Skin Formation	DBTM 10.00	15 minutes @ +23°C/50% RH
Shore A Hardness	DIN 53505	55
Temperature Resistance		-40°C to +90°C

These values are typical properties and may vary +/-3%

**Shelf Life**

In unopened original packaging between + 5°C and + 25°C, shelf life is up to 18 months from production date, stored in a dry place.

**Health & Safety**

Safety data sheet (MSDS) must be read and understood before use of product. These are available on request.

